



CROHMIQ® Static Protective FIBC Fabric (ultrasonic slit edge)

6.5 oz/yd² Coated

TYPICAL DATA SHEET

<u>Typical Properties</u>	<u>Test Method</u>	
• Fabric		Polypropylene
• Coating ⁽¹⁾		1.5 Mil PP/PE
• Color		White with blue highlight yarns
• Standard Widths		Inches: 36, 42, 45 and 48 cm: 91, 107, 114 and 122
• Construction		19 EPI x 12 PPI ⁽³⁾
• Weight		7.0 oz/yd ² Uncoated Minimum 238 g/m ² Uncoated Minimum 8.0 oz/yd ² Coated Typical 272 g/m ² Coated Typical
• Tensile Strength, lbs.	ASTM D-4632	300 x 300 ⁽²⁾
• Elongation, %	ASTM D-4632	23 x 18 ⁽³⁾
• Trapezoid Tear Strength, lbs.	ASTM D-4533	120 x 120 ⁽³⁾
• Puncture, lbs.	ASTM D-4833	150 ⁽³⁾
• Mullen Burst Strength, PSI	ASTM D-3786	650 ⁽³⁾
• UV Resistance Strength Retention, %	ASTM D-4355	>70% After <u>1200</u> Hours Exposure

(1) FIBC made from CROHMIQ® static protective Type D FIBC fabrics may be used as intended for bulk storage or transport of dry food, and such use may properly be said to comply fully with the US Federal Food, Drug and Cosmetic Act and EU Directive 2002/72/EC for Plastic Materials & Articles Coming into Contact with Food.

(2) The above properties are Minimum roll averages based on uncoated test data only.

(3) The above properties are typical averages based on uncoated test data only.

Date: May 1, 2007. This data sheet supersedes all previously issued data sheets.

TEXENE is a trademark of TEXENE LLC, Summerville, SC, USA.

CROHMIQ, CROHMIQ blue, CROHMIQ white and the blue fabric color are additional registered trademarks of TEXENE LLC.

US patents 5,478,154; 5,679,449 and 6,112,772, and additional foreign patents and patent pending.

©2007 TEXENE LLC.

All Rights Reserved.

The information on this data sheet relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any other process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled. No representation, warranty, or guarantee, however, is made as to the accuracy, reliability, or completeness. Nothing herein shall be construed as creating any express or implied warranty, including but not limited to any implied warranty of merchantability or implied warranty of fitness. It is the user's responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. TEXENE LLC does not accept liability for any loss or damage that may occur from the use of this information.